



NICKEL

ANTI-SEIZE



FEATURES

- Contains no lead, copper or graphite
- Prevents seizure up to 2600°F (1427°C)
- Protects against rust and corrosion
- For use in hostile environments and extreme temperatures
- Acid resistant
- Strong resistance to water washoff
- Brushable to -18°F (-27°C)
- Will not run, drip or settle out
- Conforms to MIL-PRF-907E
- Silver color

PACKAGES

Net Fill

- 1/2 lb. (227 grams) paste
- 1 lb. (454 grams) paste

Conforms to: MIL-PRF-907E

Part No.

- 03908
- 03910

APPLICATIONS

- Bushings
- Chains
- Engines
- Flanges
- Furnaces
- Heat Exchangers
- Manifolds
- Nuts/Bolts
- Reactors
- Screws
- Studs
- Taps
- Turbines
- Valve Stems

PROPERTIES

Color/Appearance:

Silver/Gray Paste

Dropping Point (ASTM D-566):

450°F (232°C)

Flash Point (ASTM D-92):

> 430°F (221°C)

Oil Separation, Wt. % Loss

@ 212°F (100°C):

<5.0

Penetration @ 77°F ASTM D-217:

285-315

Salt Fog Resistance (ASTM B-117)

20%NaCl @ 100°F (38°C)

Hrs. Free of Corrosion:

200 +

Shell 4-Ball (ASTM D-2596)

Weld Point kgf:

200

Specific Gravity (Water = 1):

1.0-1.2 @ 68°F (20°C)

Coefficient of Friction:

0.15



MATERIAL SAFETY DATA SHEETS AVAILABLE UPON REQUEST OR VISIT OUR WEB SITE :WWW.LPSLABS.COM

LPS Laboratories • An Illinois Tool Works Company

P.O. Box 105052 • 4647 Hugh Howell Road • Tucker, GA 30085-5052 • TEL: (800) 241-8334 or (770) 243-8800 • FAX: (800) 543-1563 or (770) 243-8899

Internet Web Site: www.lpslabs.com

©2010 LPS Laboratories • LPS® is a registered trademark of Illinois Tool Works • Printed in U.S.A. • All Rights Reserved • Form #2110 • Rev. 11/2010