


ALKALINE-MANGANESE DIOXIDE BATTERY





Dimensions shown are IEC standards

KEY FEATURES

- Reliable Performance
- Excellent resistance to corrosion
- Designed to meet all major quality, safety and environmental standards:
 - o Safety: IEC 60086-5
 - o ANSI C 18.1M, Part-2
 - EU Battery Directive
 - Quality: ISO 14001 and 9001, Duracell World Class Continuous Improvement Program

TYPICAL APPLICATIONS

- Security Keypads
- Sensors
- Flushometers

ELECTRICAL CHARACTERISTICS

| Nomina | capacity (25 Ω Cont., .8V cut-off) | 15,476 mAh |
|----------------------------|---|------------|
|----------------------------|---|------------|

- Typical Voltage (at + 20 °C)
 1.5 V
- AC Impedance @ 1kHz 136 mΩ

PHYSICAL CHARACTERISTICS

| | Typical weight | 139.0 g (4.9 oz) |
|---|----------------|---|
| • | Typical volume | 56.4 cm ³ (3.4 in ³) |
| | Terminals | Flat |

OPERATING & STORAGE CONDITIONS

| • | Operating temperature range | -20°C to 54°C (-4°F to 130°F) |
|---|--|----------------------------------|
| • | Recommended Storage (storage area should be clean, cool, dry and ventilated) | 5°C to 30°C (41°F to 86° F) |





Procell Professional batteries Berkshire Corporate Park Phone: 1-800-544-5454 (Toll-free) www.procell.com Delivered capacity is dependent on the applied load, operating temperature and cut-off voltage. Please refer to the charts and discharge data shown for examples of the energy/service life that the battery will provide for various load conditions.

This data is subject to change. Performance information is typical. Contact Duracell for the latest information.

PROCELL®

TYPICAL PERFORMANCE







PROFESSIONAL BATTERIES Procell Professional batteries Berkshire Corporate Park Phone: 1-800-544-5454 (Toll-free) www.procell.com Delivered capacity is dependent on the applied load, operating temperature and cut-off voltage. Please refer to the charts and discharge data shown for examples of the energy/service life that the battery will provide for various load conditions.

This data is subject to change. Performance information is typical. Contact Duracell for the latest information.

Zn / MnO₂