



LOCTITE[®] 540[™]

September 2005

PRODUCT DESCRIPTION

LOCTITE[®] 540[™] provides the following product characteristics:

Technology	Acrylic
Chemical Type	Methacrylate ester
Appearance (uncured)	Blue liquid ^{LMS}
Fluorescence	Positive under UV light ^{LMS}
Components	One component - requires no mixing
Viscosity	Medium, thixotropic
Cure	Anaerobic
Application	Sealing
Strength	High

LOCTITE[®] 540[™] is a thixotropic anaerobic sealant designed for sealing core plugs and many other high strength sealing applications where non-migration is desired. This product is easily applied with LOCTITE[®] applicators and prevents rusting in the threaded engagement area. Applications include sealing and securing cylindrical metal assemblies, e.g. engine block cup and core plugs, water pump seals, and hub and shaft assemblies. The thixotropic nature of LOCTITE[®] 540[™] reduces the migration of liquid product after application to the substrate. This product is typically used in applications with an operating range of -54 °C to 149 °C.

TYPICAL PROPERTIES OF UNCURED MATERIAL

Specific Gravity @ 25 °C	1.08
Flash Point - See MSDS	
Viscosity, Brookfield - RVF, 25 °C, mPa·s (cP):	
Spindle 5, speed 2.0 rpm	25,000 to 45,000 ^{LMS}
Spindle 5, speed 20 rpm	7,000 to 12,000 ^{LMS}

TYPICAL PROPERTIES OF CURED MATERIAL

Physical Properties:

Coefficient of Thermal Expansion, ASTM D 696, K ⁻¹	0.1
Coefficient of Thermal Conductivity, ASTM C177, W/(m·K)	0.1
Specific Heat, kJ/(kg·K)	0.3

TYPICAL PERFORMANCE OF CURED MATERIAL

Cured for 1 hour @ 22 °C

Compressive Shear Strength, ISO 10123: Steel pins and collars	N/mm ² ≥5.5 ^{LMS} (psi) (≥797)
--	---

Cured for 24 hours @ 22 °C

Compressive Shear Strength, ISO 10123: Steel pins and collars	N/mm ² ≥14.0 ^{LMS} (psi) (≥2,030)
--	--

Cured for 48 hours @ 22 °C, followed by 2 hours @ 88 °C, tested @ 88 °C

Compressive Shear Strength, ISO 10123: Steel pins and collars	N/mm ² ≥13.8 ^{LMS} (psi) (≥2,001)
--	--

Cured for 48 hours @ 22 °C followed by 120 hours @ 121 °C, tested @ 22 °C

Compressive Shear Strength, ISO 10123: Steel pins and collars	N/mm ² 13.8 (psi) (2,001)
--	---

GENERAL INFORMATION

This product is not recommended for use in pure oxygen and/or oxygen rich systems and should not be selected as a sealant for chlorine or other strong oxidizing materials.

For safe handling information on this product, consult the Material Safety Data Sheet (MSDS).

Where aqueous washing systems are used to clean the surfaces before bonding, it is important to check for compatibility of the washing solution with the adhesive. In some cases these aqueous washes can affect the cure and performance of the adhesive.

This product is not normally recommended for use on plastics (particularly thermoplastic materials where stress cracking of the plastic could result). Users are recommended to confirm compatibility of the product with such substrates.

Directions for use

For Assembly

1. For best performance bond surfaces should be clean and free from grease
2. For maximum bond strength apply adhesive evenly to both surfaces to be joined
3. Parts must be closely-fitted metal surfaces in order to assure effective sealing and bonding of the assembly.
4. Assemble parts in accordance with standard practice.
5. The bond should be allowed to cure 24 hours before subjecting to heavy service loads
6. To get a fast seal against high pressure and chemicals, treat the parts with Activator 7471[™] before assembly.

For Disassembly

1. Where hand tools do not work because of excessive engagement length or large diameters (over 25.4 mm), apply localized heat to approximately 250 °C. Disassemble while hot.

Loctite Material Specification^{LMS}

LMS dated September 1, 1995. Test reports for each batch are available for the indicated properties. LMS test reports include selected QC test parameters considered appropriate to specifications for customer use. Additionally, comprehensive controls are in place to assure product quality and consistency. Special customer specification requirements may be coordinated through Henkel Quality.

Storage

Store product in the unopened container in a dry location. Storage information may be indicated on the product container labeling.

Optimal Storage: 8 °C to 21 °C. Storage below 8 °C or greater than 28 °C can adversely affect product properties.

Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel Corporation cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Technical Service Center or Customer Service Representative.

Conversions

$(^{\circ}\text{C} \times 1.8) + 32 = ^{\circ}\text{F}$

$\text{kV/mm} \times 25.4 = \text{V/mil}$

$\text{mm} / 25.4 = \text{inches}$

$\mu\text{m} / 25.4 = \text{mil}$

$\text{N} \times 0.225 = \text{lb}$

$\text{N/mm} \times 5.71 = \text{lb/in}$

$\text{N/mm}^2 \times 145 = \text{psi}$

$\text{MPa} \times 145 = \text{psi}$

$\text{N}\cdot\text{m} \times 8.851 = \text{lb}\cdot\text{in}$

$\text{N}\cdot\text{m} \times 0.738 = \text{lb}\cdot\text{ft}$

$\text{N}\cdot\text{mm} \times 0.142 = \text{oz}\cdot\text{in}$

$\text{mPa}\cdot\text{s} = \text{cP}$

Note

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Trademark usage

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

Reference 1.0