

PHYSICAL PROPERTIES

Product	Backing	Adhesive	Total thickness (mils)	Tensile strength (lb/in of width)	Adhesion to steel (oz/in of width)	Elongation (% at break)	Temperature resistance	Color
PG	Fine crepe paper	Natural rubber/resin	7.3 (0.19mm)	26 (114 N/25mm)	28 (7.7 N/25mm)	10	250°F (121°C) 30 min	Beige
OM	Fine crepe paper	Natural rubber/resin	7.1 (0.18mm)	23 (101 N/25mm)	27 (7.4 N/25mm)	12	250°F (121°C) 30 min	Orange
AM	Saturated crepe paper	Natural rubber/resin	6.6 (0.17mm)	20 (87.5 N/25mm)	28 (7.6 N/25mm)	12	225°F (107°C) 30 min	Aqua (blue-green)
MP	Crepe paper	Natural rubber	6.1 (0.155mm)	25 (109.5 N/25mm)	33 (9 N/25mm)	8	250°F (121°C) 1 hour	Beige
UG	Coarse crepe paper	Natural rubber	6.3 (0.16 mm)	21 (92 N/25mm)	32 (8.8 N/25mm)	14	175°F (80°C) 30 min	Beige
FM35	Blue PVC	Natural rubber	5.4 (0.14mm)	15 (65.6 N/25mm)	23 (6.3 N/25mm)	150	40°F to 280°F (4.4°C to 138°C) (operating range)	Light Blue Low Gloss

PG	Resource Number	Size	Rolls per Case		
	PG1855	18mm x 54.8m	48 rolls		
	PG2455	24mm x 54.8m	36 rolls		
	PG3655	36mm x 54.8m	24 rolls		
	PG4855	48mm x 54.8m	24 rolls		
OM	Resource Number	Size	Rolls per Case		
	OM1855	18mm x 54.8m	48 rolls		
	OM2455	24mm x 54.8m	36 rolls		
	OM3655	36mm x 54.8m	24 rolls		
	OM4855	48mm x 54.8m	24 rolls		
AM	Resource Number	Size	Rolls per Case		
	AM1855	18mm x 54.8m	48 rolls		
	AM2455	24mm x 54.8m	36 rolls		
	AM3655	36mm x 54.8m	24 rolls		
	AM4855	48mm x 54.8m	24 rolls		
MP	Resource Number	Size	Rolls per Case		
	MP1855	18mm x 54.8m	48 rolls		
	MP2455	24mm x 54.8m	36 rolls		
	MP3655	36mm x 54.8m	24 rolls		
	MP4855	48mm x 54.8m	24 rolls		
UG	Resource Number	Size	Rolls per Case		
	UG1850 (88400)	18mm x 50m	48 rolls		
	UG2450 (88401)	24mm x 50m	36 rolls		
	UG3650 (88402)	36mm x 50m	24 rolls		
	UG4850 (88403)	48mm x 50m	24 rolls		
FM35	Resource Number	Size	Rolls per Case		
	FM35..3	3mm x 33m	360 rolls		
	FM35..6	6mm x 33m	168 rolls		
	FM35..9	9mm x 33m	108 rolls		
	FM35..12	12mm x 33m	78 rolls		