

Elbows, Sweeps and Accessories

RECOMMENDED PIPE VISCOSITY AT 75° F APPLICATION AND SIZES	SET-UP TIME (EVAPORATION RATE)	RECOMMENDED INSTALLATION TEMP.	LAP SHEAR @ 73° F	VISCOSITY AT 75° F AS MANUFACTURED
Recommended for all grades and types of Carlton® wireway and fittings, except Flex-Plus® Blue™ ENT (Electrical Non-Metallic Tubing).	10°–30° F Not recommended 30°–50° F 5–6 minutes 50°–70° F 3–4 minutes 70°–90° F 1–2 minutes	40° to 100° F	2 hrs. 350 psi 16 hrs. 800 psi 72 hrs. 1,500 psi	500–900 cps

Up through 6" diameter.

Low-VOC Medium — Clear

CAT. NO.	SIZE	APPLICATOR	DESCRIPTION	STD. CTN.	STD. WT. (LBS.)
VC9963	Pint	Dauber	PVC Medium Clear	24	29.0
VC9962	Quart	Dauber	PVC Medium Clear	12	27.5
VC9961P	Gallon	—	PVC Medium Clear	6	53.5

Meets ASTM D-2564.



Low-VOC Medium — Gray

CAT. NO.	SIZE	APPLICATOR	DESCRIPTION	STD. CTN.	STD. WT. (LBS.)
VC9923	Pint	Dauber	PVC Medium Gray	24	29.0
VC9922	Quart	Dauber	PVC Medium Gray	12	27.5
VC9941P	Gallon	—	PVC Medium Gray	6	53.5

Meets ASTM D-2564.



Low-VOC Regular — Clear

CAT. NO.	SIZE	APPLICATOR	DESCRIPTION	STD. CTN.	STD. WT. (LBS.)
VC9964	Half Pint	Dauber	PVC Regular Clear	10	29.0

Meets ASTM D-2564.

Note: Rated for Schedule 40 through 4" and Schedule 80 through 2".



Low-VOC Regular — Gray

CAT. NO.	SIZE	APPLICATOR	DESCRIPTION	STD. CTN.	STD. WT. (LBS.)
VC9924-24	Half Pint	Dauber	PVC Regular Gray	24	15.0

Meets ASTM D-2564.



Clear Primer

CAT. NO.	SIZE	APPLICATOR	STD. CTN.	STD. WT. (LBS.)
VC9903	Pint	Dauber	24	27.0
VC9902	Quart	Dauber	12	25.0

Meets ASTM F-686.



Purple Primer

CAT. NO.	SIZE	APPLICATOR	STD. CTN.	STD. WT. (LBS.)
VC9932	Quart	Dauber	12	25.0

Meets ASTM F-686.



RECOMMENDED PIPE APPLICATION AND SIZES	RECOMMENDED INSTALLATION TEMPERATURE
Recommended for use with Carlton® cement	5° to 100° F

RECOMMENDED PIPE APPLICATION AND SIZES	RECOMMENDED INSTALLATION TEMPERATURE
Recommended for use with Carlton® cement	5° to 100° F